



EASYSET™ 20

Quick Drying | Smooth Finishing | Multi-Purpose Compound

EASYSET™ 20

EasySet™ 20 is a powdered compound suitable for walls and ceiling. It is best used for taping, bedding and as a finishing coat for fibrous plaster's and gypsum board's joint. Its smooth texture makes it easy to apply and sand while the EasySet™ 20's quick setting time allows for same-day joint finishing.

Jointing Compound

PRODUCT INFORMATION



Compound Type	Setting type powdered compound
Mixing Ratio	1 part water, 2 parts of powder
Packaging	20kg bag
Setting Coverage	65m ² per 20kg bag (based on 3 coats application method.)
Storage	EasySet™ 20 must be stored under cover in a dry environment and protect from freezing temperatures and direct sunlight.
Shelf Life	Best before 6 months (from production date).

PREPARATION

Mixing EasySet™ 20

1. Always use clean cold water, clean containers and tools.
2. Using dirty containers/water/tools may affect setting time and set strength.
3. For best results, slowly add powder to water and allow powder to soak 1-3 minutes before mixing.
4. Mix only enough compound for 20 minutes working time.
5. Mix by hand or with a power mixer (max. of 400rpm) - mixing at higher speeds will draw air into the mix and may affect working time. Mix until a smooth workable paste has been achieved.
6. Once setting has commenced, the material cannot be remixed and should not be used further. The inclusion of other materials (e.g. retarders, fillers, etc.) in the mix will impair the performance of this product, i.e. reduced strength, poor adhesion and will void the product warranty.

APPLICATION

Applying EasySet™ 20

First Coat (150mm wide)

1. Using a broad knife, evenly fill the joint recess formed by the edges of the plasterboard with EasySet™ 20.
2. Centre paper tape along the joint and press into the compound using the broad knife.
3. Draw the broad knife at a 45° angle along the joint with enough pressure to remove excess compound and any air bubbles caught beneath the tape. Leave enough compound under the tape to provide a strong bond.
4. Apply a thin layer of compound over the tape to prevent the tape edge curling and cracking. Feather the compound from the edges outwards. Cover all fastener heads with spots of compound.

Second Coat (200mm wide)

5. When dry, apply a second coat using a plasterer's trowel, approximately 50mm wider than the first coat. Spot fastener heads again. Allow to dry.
6. When the second coats has dried, scrape or sand back any excess compound for a smooth and level surface.

Third Coat (275mm wide)

7. Apply a finishing coat of compound with a trowel, approximately 75mm wider than the previous coat.
8. When dry, using 150 to 180 grit sandpaper in a hand sander, sand lightly to a smooth finish, taking care not to scuff the surrounding plasterboard.



1ST COAT



2ND COAT



FINISHING COAT



SANDABLE

TRADEMARKS

The trademarks USG BORAL and INNOVATION INSPIRED BY YOU are trademarks of USG Boral Building Products or one of more of its affiliates.

SAFETY FIRST

Follow good safety/industrial hygiene practices during installation. Wear appropriate personal protective equipment. Read SDS and literature before specification and installation.

© 2017 USG Boral. All rights reserved.

Manufactured, sold or distributed by USG Boral Building Products or one or more of its affiliates, Persiaran Lagoon, Bandar Sunway, Petaling Jaya, Selangor, Malaysia 46150.

USG BORAL SINGAPORE

8 Boon Lay Way #02-06 TradeHub 21
Singapore 609964
Tel: (+65) 6272 9272 Fax: (+65) 6278 5310

USGBoral.com

USG Boral Sdn Bhd (Singapore Branch) doing business as USG Boral Singapore.

USG BORAL
INNOVATION INSPIRED BY YOU™